



Fasatan TFS Adhesive Sealant

Fasatan® TFS is suitable for internal and external elastic bonding:

- for the bonding of our construction sealing membranes Fasatan® and Fasatyl®,
- for the bonding of rebates, mitres and overlaps,
- for internal and external joint sealing,
- for bonding of construction components made from plaster, natural stone, aluminium, steel, zinc, copper, glass, wood, MDF, tiles, ceramic among each other or on solid mineral subsurfaces.

Fasatan® TFS is a flexible, single-component adhesive sealant. Fasatan® TFS is resistant to overnight condensation and cures with atmospheric moisture to a flexible, rubbery plastic. This has excellent weather and chemical resistance.

Technical Information

- Very rapid and secure working,
- free of solvent and neutral in odour and resistant to overnight condensation,
- offers a wide spectrum of adhesion to concrete, aluminium blank and powder coated, unplasticised PVC, wood as well as many other normal building materials,
- good adhesion force also on many solvent sensitive subsurfaces,
- processing possible from – 5 °C on under destined conditions,
- single-sided adhesive application and no pre-treatment of the membrane,
- adjustment possibilities for laminate up to 30 minutes after adhesion,
- possesses excellent weather, UV and chemical resistance.

Processing Notes

Depending on underground about 10 m per 600 ml tubular bag, nozzle diameter 8mm. At 1 mm layer thickness of the adhesive the consumption is approx. 1 l / m², i.e. a 600 ml tubular bag suffices for approx. 0.6m² adhesion surface. The internal seal must be more vapour diffusion tight than the outer seal. Therefore Fasatan® must be used for the outer seal and Fasatyl® for the inner seal. Care must be taken during sealing that the joint space is first well insulated with suitable material (mineral wool or other) to avoid heat bridges and undershooting the dew point on the inside.



Technical Data

| | |
|-----------------------------|--|
| Basis | silane terminated polymer |
| Colour | black |
| Curing System | atmospheric humidity |
| Transfer Rate | > 100g/min, DIN52 456 - 6mm |
| Spec. weight | approx. 1.5g/cm ³ , DIN52 451 - PY |
| Skin formation time | approx. 1h, +23C / 50% r.h. |
| Curing | approx. 2mm/24h, +23C / 50% r.h. |
| Volume change | < -3%, DIN52 451 - PY |
| Stress-strain value at 100% | approx. 0.4N/mm ² , DIN52 455 NWT |
| Tensile strength | approx. 1.0N/mm ² , DIN53 504 |
| Shore A Hardness | approx.25, DIN53 505, 4 weeks +23C |
| Permissible net deformation | 25% |
| Temp. resistance | -40C to +80C |
| Processing temp. | +5C to +40C, verified by cert. from MPA, under destined conditions |

UK Passive House Systems Ltd.
Epping, Essex, CM16 6TH
Tel:08454591500
Website www.passivehousesystems.co.uk

Ireland. Passive House Systems.
Aherla, Co. Cork, Ireland
Tel: (00353) 021 4289407
Website www.passivehousesystems.ie

Passive House Systems products are used by a very diverse customer base for a wide range of technical and industrial applications. The demands made on our products vary considerably from application to application. We strongly advise users to test the products suitability for their own particular requirement. All data and recommendations contained in this Technical Data Sheet are based on our own test results and practical experience and are aimed at helping customers select the appropriate product. This information is provided without liability. We reserve the right to change the technical specification without prior notice. Samples are available free of charge. Our sales team is also available to assist customers with their help.